



# VLP®

## VINYL / LEATHER REPAIR

### DESCRIPTION:

VLP® is a clear, high strength, tear repair, designed to mend rips, tears and small holes on most types of flexible vinyl surfaces. VLP® is supplied in an easy to use, air dry formula that dries clear and blends with all colored vinyls. VLP® actually dissolves the surface of the vinyl and creates an excellent bond when completely dry. On porous fabrics, VLP® can be used the same as on vinyl but actually penetrates the pores and creates an excellent mechanical bond. VLP® is typically used on vinyl furniture, awnings, tarps, vinyl sheeting, luggage, rain wear, boots, etc. Because of its' bonding and tensile strength, VLP® also acts as a "back up" to sewn vinyl seams when applied to the backside of the seam in production.

### SPECIFICATIONS:

Solids: (wt) 18%  
Temperature use range: -10°F to 200°F  
Tensile: (ASTM D-882) 2,900psi  
Bond strength: (ASTM D-882) 26.02 # load  
Elongation: (ASTM D-882) 240%  
Dry color: clear  
Viscosity range: 1,200-2,500 cps  
Coverage: 60 sq. ft. per gal at 5 mils  
Shelf life: 1+ year at 77°F

### ALTERNATIVE PRODUCTS:

For patching or swimming pool liner repairs, use Performix Brand® VYNA BOND. For ultimate surface to surface adhesion of vinyls and other materials, see VYNA BOND technical data sheet #2.

### SURFACE PREPARATION:

All surfaces to be glued must be free of all oils, dust or other foreign matter. **Lightly wipe down vinyl with alcohol and let dry.**

### USE ADEQUATE VENTILATION.

Plasti Dip International  
3920 Pheasant Ridge Drive  
Blaine, MN 55449  
Phone: 800-969-5432  
Fax: 763-785-2058



**CAUTION:** If VLP® is smeared on vinyl, it can discolor or remove colorant from vinyl.

Directions:

1. Small tears and splits require a light bead application of VLP®. Allow 30 minutes to dry and repeat. Allow 4 hours dry time for maximum strength.
2. Long tears and splits require the vinyl to be pulled together and stitched with masking tape every 1" to 2". Apply a light bead application of VLP® to untaped areas and allow a minimum of 4 hour to dry. Carefully remove masking tape and apply a light bead application to entire repair. Allow 4 hours dry time before use or 4 hour and repeat; then allow 4 hours dry time for maximum strength.
3. For small holes: Apply a few drops of VLP® and allow to dry 1 hour before use.
4. To conceal repair, apply a small amount of VLP® to a lint free cloth and dab lightly onto dried VLP® repair until gloss is removed.
5. For large holes: Use Performix Brand® VYNA BOND.

**HINTS:**

Recommended thinners are Methyl Ethyl Ketone and THF. Allow to dry overnight whenever possible. Do not smear VLP® on colored vinyls. Apply in temperatures above 50°F. Avoid excessive air movement, heat or humidity. Always use proper ventilation and protection.

**Athletic Equipment**

**Bowling bags**

**Golf bags**

**Covers**

**Tent Floors**

**Rainwear**

**Curtains**

**Awnings**

**Vinyl welting**

**Luggage**

**Garment bags**

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

VLP, Performix and logo are registered trademarks of PLASTI DIP INTERNATIONAL

VLP TECHNICAL DATA SHEET #1  
REVISED 6/19/2008 – DD